








**ACROPOLI 4064** ■ ■ FULLY  
MADE IN ITALY

COMPOSITION: ..... 55 %VI 19%CO 15%PL 09%PC 02%VD  
HAIR: ..... 100%VI  
WIDTH: ..... 105-110 cm  
WEIGHT: ..... 1460 gr/mtl

USE:  

CARE:       
IRON ON REVERSE

ABRASION RESISTANCE (MARTINDALE END POINT): ..... 80.000 rubs  
UNI EN ISO 12947-2:2000 12 kPa

COLOUR FASTNESS TO LIGHT: ..... 5  
UNI EN ISO 105-B02:2004

COLOUR FASTNESS TO CROKING: ..... dry 5 wet 4/5  
UNI EN ISO 105:X12

DIMENSIONAL STABILITY TO DRY-CLEANING: ..... shortening shrinkage  
UNI EN ISO 3175-2:2010  
after dry cleaning - 1,10% 0,40%  
after ironing - 0,90% 0,50%

CHARACTERISTICS: Quilted velvet - Viscose velvet - 3D

MINIMUM ORDER QUANTITY: ..... 1 mt

CUSTOMISED COLOUR: ..... 60 mt

All intellectual property rights in our design and in innovative structure yarn and finishing are and will remain the property of Decobel srl, any infringement of this rights will be pursued vigorously.

12 | 01 | 02 | 10 | 04 | 08 | 19 | 22 | 15 | 25

