



ERACLE 4130

 FULLY
MADE IN ITALY

COMPOSITION: 93%CO 7%PL
HAIR: 100%CO
WIDTH: 140 cm
WEIGHT: 990 gr/mtl



ABRASION RESISTANCE (MARTINDALE END POINT): > 200.000 rubs
UNI EN ISO 12947-2:00 12 kPa

COLOUR FASTNESS TO LIGHT: 5
UNI EN ISO 105-B02:2004

COLOUR FASTNESS TO CROKING: dry 5 wet: 4/5
UNI EN ISO 105:X12

DETERMINATION OF SPLIPPAGE RESISTANCE: weft/warp 3,3mm
UNI EN ISO 13936-2:2004 warp/weft 3mm

COLOUR FASTNESS TO DRY CLEANING: Colour change 5
(perchloroethylene solvent) 4/5
UNI EN ISO 105 D01:2010 AC 4/5
CO 4/5
PA 4/5
PL 4/5
PC 4/5
WO 4/5

COLOUR FASTNESS TO WATER: Colour change 5
UNI EN ISO 105 E01:2013 AC 4/5
CO 4/5
PA 4/5
PL 4/5
PC 4/5
WO 4/5

CHARACTERISTICS:

MINIMUM ORDER QUANTITY: mt

CUSTOMISABLE COLOR MINIMUM ORDER QUANTITY: mt

TEST IGNIFUGHI

 BS5852-1:1979 Cigarette using filling material
PU non FR (20-22 Kg/m³) SS20

 EN 1021-1:2006 Cigarette using filling material
PU FR HR30S (30-33 K/m³)

All intellectual property rights in our design and in innovative structure yarn and finishing are and will remain the property of Decobel srl. any infringement of this rights will be pursued vigorously.

