

# WOOL DREAM 4332



COMPOSITION

72% WV 28% PL

PILE COMPOSITION

100% WV - 100% Natural Fibers

WIDTH

140 cm

WEIGHT

870-890 gr/mtl

USE



CARE



ABRASION RESISTANCE END POINT

50.000 rubs

UNI EN ISO 12947-2:2000 12KPA

COLOUR FASTNESS TO LIGHT 4/5

UNI EN ISO 105-BO2:2004

PILLING TEST

4/5

UNI EN ISO 12945-2 5000 RUBS

DETERMINATION OF SLIPPAGE RESISTANCE

UNI EN ISO 13936-2:2004

Weft/Warp < 3 mm

Warp/Weft < 3 mm

DETERMINATION OF TEAR FORCE

WING-SHAPED TEST SPECIMENT

UNI EN ISO 13937-3

Warp 34 N

Weft 32,3 N

FLAMEPROOF TEST

Cigarette test EN 1021 - 1

Pass

Match test EN 1021 - 2

Pass

Cigarette test BS 5852 - 1 sch.4 part 1

Pass

Match test BS 5852-1 sch. 5 part 1

Pass

California TB 117 : 2013 + 2015

Pass



All intellectual property rights in our design and in innovative structure yarn and finishing are and will remain the property of Decobel srl. Any infringement of this rights will be pursued vigorously.

© Icons from Noun Project - Yusuf - Azam Ishaq - Youngky Kurniawan (CC BY 3.0)